

Raw Materials for Refractory Industries

Code	CS-20
	Calcined Fire clay (CHAMOTTE)
	Chemical Analysis
SiO₂	50-51
Al₂O₃	42-43
Fe₂O₃	≤ 1
TiO₂	<2
CaO	<0.3
MgO	0.6
K₂O+ Na₂O	<0.8
L.O.I	<0.15
Bulk Density	2.65-2.75
%Water absorption	1
Application	Refractory products
Available Size	0-30 / 4.8-2.4/2.4-1.2 /1.2-0.6 /≤0.1/≤0.6 mm
Delivery place	Tehran
Packing	Bulk-Big bag



Suravajin Aghigh Mining & Industrial CO

Office: 3rd floor, No.82, Ebnesina, Yousef Abad, Tehran 1433863595 – Iran - Telefax: +98(21) 88105230-8107252

info@iranclay.ir www.iranclay.ir